

Chatsworth - worn

Derbyshire Limestone

Medium to coarse grained Limestone with exceptional durability.

Technical data sheet

Please note - stone is a natural product and is subject to variation in colour, tone and texture. Below is a selection of photos showing typical variation we would expect from this stone type.



| | |
|-------------------------------|---|
| Country of Origin | UK |
| Quarry Location | Derbyshire |
| Geological Type | Limestone |
| Colour | Light to dark greys, occasional pink tones and distinctive fossils. |
| Density | 2650kg/ m3 |
| Flexural Strength | 12.4 MPa |
| Slip Resistance | 48 - Wet 28 - Dry |
| Porosity | 0.8% |
| Saturation Coefficient | 0.96% |
| Water Absorption | 0.27% |
| Freeze/Thaw Loss | 0.1% |



ALLGREEN

01935 415560
sales@allgreen.uk
www.allgreen.uk

Please note stone is a natural product and these results are subject to variation.