

Compton - Sawn

Yorkshire Sandstone

Fine grained sandstone. Durable building and paving stone.

Technical data sheet

Please note - stone is a natural product and is subject to variation in colour, tone and texture. Below is a selection of photos showing typical variation we would expect from this stone type.



Country of Origin	UK
Geological Type	Carboniferous York stone
Colour	Grey with occasional hint of brown.
Density	2380kg/m ³
Compression Strength	126.42 MPa
Water Absorption	3.89%
Porosity	10.9%
Durability	Good slip and abrasion resistance suitable for high traffic areas. Tests indicate a slight susceptibility to very harsh salt environments such as coastal areas.
Flexural Strength (after freeze/thaw test)	12.6 MPa
Slip Resistance	85 Dry



ALLGREEN

01935 415560
sales@allgreen.uk
www.allgreen.uk