


Compton - worn

Yorkshire Sandstone

Fine grained sandstone. Durable building and paving stone.

Technical data sheet

Please note - stone is a natural product and is subject to variation in colour, tone and texture. Below is a selection of photos showing typical variation we would expect from this stone type.



| | |
|---|--|
| Country of Origin | UK |
| Geological Type | Carboniferous York stone |
| Colour | Grey with occasional hint of brown. |
| Density | 2380kg/m ³ |
| Compression Strength | 126.42 MPa |
| Water Absorption | 3.89% |
| Porosity | 10.9% |
| Durability | Good slip and abrasion resistance suitable for high traffic areas. Tests indicate a slight susceptibility to very harsh salt environments such as coastal areas. |
| Flexural Strength (after freeze/thaw test) | 12.6 MPa |
| Slip Resistance | 85 Dry |



ALLGREEN

01935 415560
sales@allgreen.uk
www.allgreen.uk