

Darley Buff



Technical Results

Description	Fine to medium grained Sandstone. Durable with good weathering qualities.
Quarry Location	West Yorkshire, UK
Geological Type	Carboniferous Sandstone
Colour	Pale buff with occasional gold/brown variation.
Density	2416 kg/m ³
Slip Resistance	75-83
Abrasion Resistance	19.6mm
Compression	132 MPa
Bending Strength	15-18.9 MPa
Porosity	8.6-9.2%
Water Absorption	2.4%
Flexural strength after freeze/thaw test	14.3 MPa



Allgreen Group
46 Buckland Road
Pen Mill Trading Estate
Yeovil
Somerset
BA21 5EL

+44(0)1935 415560
sales@allgreengroup.co.uk

Please note stone is a natural product and these results are subject to variation.