

Haslingden - *sawn*

Yorkshire Sandstone

Fine grained Sandstone. Durable building and paving stone.

Technical data sheet

Please note - stone is a natural product and is subject to variation in colour, tone and texture. Below is a selection of photos showing typical variation we would expect from this stone type.



Country of Origin	Yorkshire, UK	
Geological Type	Carboniferous Sandstone	
Colour	Light Buff	
Density	2313kg/m ³	
Compression Strength	73.2 MPa	BDS EN 1926:2008
Flexural Strength	13.0 MPa	BDS EN 12372:2008
Water Absorption	4.3%	BDS EN 13755:2008
Porosity	14.2%	
Frost Resistance	9.3 MPa Flexural strength after 56 cycles	BDS EN 12371:2010
Slip Resistance	71 Wet 74 Dry	BDS EN 14231:2008



ALLGREEN

01935 415560
sales@allgreen.uk
www.allgreen.uk