

Haslingden - worn

Yorkshire Sandstone

Fine grained Sandstone. Durable building and paving stone.

Technical data sheet

Please note - stone is a natural product and is subject to variation in colour, tone and texture. Below is a selection of photos showing typical variation we would expect from this stone type.



| | | |
|-----------------------------|--|-------------------|
| Country of Origin | Yorkshire, UK | |
| Geological Type | Carboniferous Sandstone | |
| Colour | Light Buff | |
| Density | 2313kg/m ³ | |
| Compression Strength | 73.2 MPa | BDS EN 1926:2008 |
| Flexural Strength | 13.0 MPa | BDS EN 12372:2008 |
| Water Absorption | 4.3% | BDS EN 13755:2008 |
| Porosity | 14.2% | |
| Frost Resistance | 9.3 MPa Flexural strength after 56 cycles | BDS EN 12371:2010 |
| Slip Resistance | 71 Wet 74 Dry | BDS EN 14231:2008 |



ALLGREEN

01935 415560
sales@allgreen.uk
www.allgreen.uk