

# Moordale

## Indian Sandstone



<b>Country of Origin</b>	India	
<b>Geological Type</b>	Sandstone	
<b>Colour</b>	Tones of brown and crimson.	
<b>Compressive Strength</b>	360.1 kg/cm <sup>2</sup>	EN1926 : 1999
<b>Flexural Strength</b>	23 MPa	EN12372 : 2006
<b>Water Absorption</b>	0.93% by weight 0.28% by capillary	EN13755: 2001 EN1925: 1999
<b>Density</b>	2.52%	EN 1936 : 1999
<b>Porosity</b>	0.51%	EN 1936 : 1999
<b>Frost Resistance</b>	After 12 cycles Flex strength: 21.8 MPa After 48 cycles Flex strength 19.4 MPa	EN12372 : 2006



ALLGREEN

01935 415560  
sales@allgreen.uk  
www.allgreen.uk

Please note stone is a natural product and these results are subject to variation.