

Richmond



Technical Results

| | |
|-------------------------------|--|
| Description | Fine grained Sandstone. Durable building and paving stone. |
| Quarry Location | Bradford, West Yorkshire, UK |
| Geological Type | Carboniferous Sandstone |
| Colour | Dark brown with grey and iron variation |
| Density | 2354kg/m ³ |
| Compression Strength | 113.6 MPa |
| Water Absorption | 2.8% |
| Porosity | 11.6% |
| Durability - Frost Resistance | 10.4 MPa |
| Resistance to salt | -0.77% mean wt loss |
| Slip Resistance | 71 |



Allgreen Group
46 Buckland Road
Pen Mill Trading Estate
Yeovil
Somerset
BA21 5EL

+44(0)1935 415560
sales@allgreengroup.co.uk

Please note stone is a natural product and these results are subject to variation.